



Technical Characteristic KAI/KOS
FISA TEHNICA

ODU
16.07.05(7/0)

Model Cortes,
Internal code: 9438, 9439
Type Porcelain Tiles GL,

Group Bla, Nominal size 204x1204x10 mm

Characteristics/Caracteristici Group Bla, Annex G	Tolerance EN 14411:2016, %	Tolerance EN14411:2016, mm	Request values/Valori conform standard	Measured in KAI laboratory/Masuratori in laborator Kai	Testing method/Metoda de lucru										
1. Length/width Lungime/Latime, mm	±0.6/max±2mm	±1.20/±2.00	204x1204	<table border="1"> <tr><td>1K</td><td>203.0x1201.0</td></tr> <tr><td>2K</td><td>203.5x1202.5</td></tr> <tr><td>3K</td><td>204.0x1204.0</td></tr> <tr><td>4K</td><td>204.5x1205.5</td></tr> <tr><td>5K</td><td>205.0x1207.0</td></tr> </table>	1K	203.0x1201.0	2K	203.5x1202.5	3K	204.0x1204.0	4K	204.5x1205.5	5K	205.0x1207.0	EN ISO 10545-2
1K	203.0x1201.0														
2K	203.5x1202.5														
3K	204.0x1204.0														
4K	204.5x1205.5														
5K	205.0x1207.0														
2.Thickness Grosimea, mm	±5/max±0.5mm	±0.50	±0.50 mm	9.9 – 10.0 mm	EN ISO 10545-2										
3. Straightness of sides Liniaritatea muchiei, mm	±0.5/max±1.5mm	±1.00/±1.50	±1.00/±1.50	+0.04 – +0.20 mm	EN ISO 10545-2										
4. Centre curvature Curbura centrala, mm	±0.5/max±2mm	±2.00	±2.00	+0.14 – +0.89 mm	EN ISO 10545-2										
5. Edge curvature Curbura laterala, mm	±0.5/max±2mm	±1.00/±2.00	±1.00/±2.00	-0.10 – +1.05 mm	EN ISO 10545-2										
6. Surface quality Calitatea suprafetei	≥95% without defects	≥95% without defects	≥98% without defects	Pass	EN ISO 10545-2										
7. Water absorption Absorbția de apa, %	≤0,5% Individual ≤0,6%	≤0,50% Individual ≤0,60%	≤0,50%	0.05 – 0.24%	EN ISO 10545-3										
8. Modulus of rupture Rezistența mecanică, N/mm²	≥35N/mm² individual ≥32N/mm²	≥35N/mm² individual ≥32N/mm²	≥35N/mm²	Average: 55 N/mm²	EN ISO 10545-4										
9. Breaking strength Forța de rupere, N	≥ 1300N	≥ 1300N	≥ 1300N	Average: 3031 N	EN ISO 10545-4										
10. Determination of surface abrasion for glazed tiles/Rezistența la abraziune	the class of abrasive resistance and the number of cycles are declared by producer	the class of abrasive resistance and the number of cycles are declared by producer	Declared value	9438: 3/ 750 9439: 3/ 750	EN ISO 10545-7										
11. Craze resistance, glazed tiles/Rezistența la crașturi pentru placi glazurate	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Resistant	EN ISO 10545-11										
12. Resistance for household chemicals and swimming pool salts/Rezistența la soluțiile de uz casnic și saruriel de piscină	Min class B	Min class B	Min class B	GA	EN ISO 10545-13										
13. Resistance to the low concentration acids and alkalis/Rezistența	Declared value	Declared value	Declared value	GLA	EN ISO 10545-13										

15. Resistance to the high concentration acids and alkalis	Declared value	Declared value	Declared value	GHA	EN ISO 10545-13
16. Stain resistance	Declared value	Declared value	Min class 3	class 5	EN ISO 10545-14
17. Frost resistance	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Resistant	EN ISO 10545-12
18. Slipperiness	Declared value	Declared value	Declared value	PTV 36+ Dry PTV 0-24 Wet	CEN/TS 16165
19. MOHS	Declared value	Declared value	Declared value	8	EN 101:1991

Date: 09.07.2018

