

FISA TEHNICA
TECHNICAL DATA SHEET

Ravaproof Vapor

Caracteristici principale	Tip modificare bitum	APP		Standard tehnic armonizat
	Armatura	Fibra sticla		
	Finisaj suprafata superioara	Flim PE		
	Finisaj suprafata inferioara	Film PE		
Performante				
	Unitate de masura	Tolerante	Ravaproof Vapor	
Masa specifica	kg/m ²	±10%	1,1	EN 13707+ A2: 2010 & EN 13969:2004 EN 13969: 2007
Diametrul perforatiilor	mm	±10%	40mm	
Procent perforatii	%		16	
Masa specifica armatura fibra sticla	g/m ²	>	50	
Lungime	m	min(-0,03)	20	
Latime	cm	min(-2)	100	
Rectiliniaritate			trece	
Stabilitate dimensionala	%	max	±0,1	
Flexibilitate la rece	°C	min	0	
Punct de inmuiere	°C	min	95	
Rezistenta la tractiune (MD/CMD)	N/50mm	min	150/150	
Alungire la rupere (MD/CD)	%	min	1/1	
Rezistenta la sfasiere (testul cu cuiul)	N/50mm	±20%	NPD	
Reactia la foc	clasa		E	
Substante periculoase	on/none		fara	