

01561 Lampertswalde/Dresden Tel. +49 3522 33-30 · Fax +49 3522 33-399  $www.krono-original.com \cdot info@kronoflooring.com$ 

# **Technical Datasheet Impressions**

Made by Kronospan

Direct Pressure Laminate, Level of use according to EN 13329: class 23/32 - AC4








The guarantee applies to the living area

General commercial use according to warranty regulations\*

### **DIMENSION**









TOLERANCE				
squareness	EN 13329	≤ 0,20 mm		
straightness	EN 13329	≤ 0,30 mm		
flatness crosswise	EN 13329	concave: ≤ 0,15% · convex: ≤ 0,20%		
flatness length	EN 13329	concave: ≤ 0,50% · convex: ≤ 1,00%		
gaps between elements	EN 13329	average: ≤ 0,15 mm · max: ≤ 0,20 mm		
height difference between elements	EN 13329	average: ≤ 0,10 mm · max: ≤ 0,15 mm		
misalignment		± 2 mm		

misangriment			± 2 mm
TEST			
abrasion resistance		EN 13329	AC4 (≥ 4000 rpm)
impact resistance		EN 13329	small ball ≥ 12 N · big ball ≥ 750 mm
stain resistance	group 1 & 2	EN 13329	grade 5
	group 3		≥ grade 4
castor chair test		EN 13329	no change in appearance or damage, as defined per EN 425
effect of a furniture leg		EN 13329	no damage shall be visible, when testet with foot type 0
thickness swelling		EN 13329	≤ 18%
static indentation		EN 13329	≤ 0,05 mm
light fastness		EN 13329	grey scale ≥ 4 at blue wool grade 6
dimensional variations after changes in relative humidity		EN 13329	lengthwise ≤ 0,9 mm · crosswise ≤ 0,9 mm
locking strength		EN 13329	length ≥ 1 kN/m · width ≥ 2 kN/m
surface soundness		EN 13329	≥ 1,25 N/mm²

# **ENVIRONMENT**

emission of formaldehyde EN 717-1 Klasse E1

## PHYSICAL REHAVIOR

FRIGICAL BEHAVIOR				
fire behavior	EN 13501-1	Cfl s1		
slide resistance	EN 13893	technical class DS		
thermal resistance	EN 12667	0,073 (m <sup>2</sup> K)/W ± 15%		
thermal conductivity	EN 12664	0,110 W/(m*K) ± 15%		

\*Detailed warranty conditions are available at www.krono-original.com

For further information, please see: www.blauer-engel.de