



**Technical Characteristic KAI/KOS  
FISA TEHNICA**


ODU  
16.07.05(7/0)

**Model Latina, Internal code: 9539 and 9540 Type Tiles: Glazed Porcelain Tile GL,  
Group BIa, Nominal size 333x333x7.4 mm**

Characteristics/ aracteristici Group BIa, Annex G	Tolerance EN 14411:2016, %	Tolerance EN14411:2016, mm	Request values/Valori conform standard	Measured in KAI laboratory/Masur atori in laborator Kai	Testing method/Metoda de lucru
1.Length/width/Lu ngime/Latime, mm	±0.6/max±2mm	±2.00	333x333	3C 329,0x329,0	EN ISO 10545-2
				1C 331,0x331,0	
				0C 333,0x333,0	
				2C 335,0x335,0	
				4C 337,0x337,0	
2.Thickness/Grosi mea, mm	±5/max±0.5mm	±0.40	7.4±0.40 mm	7.1 ÷ 7.6 mm	EN ISO 10545-2
3. Straightness of sides/Liniaritatea muchiei,mm	±0.5/max±1.5mm	±1.50	±1.25 mm	-0.16 ÷ +0.26 mm	EN ISO 10545-2
4.Rectangularity/R ectangulitate, mm	±0.5/max±2mm	±1.70	±1.45 mm	-0.46 ÷ +0.79mm	EN ISO 10545-2
5. Centre curvature/Curbura centrala, mm	±0.5/max±2mm	±2.00	CC -1.5 mm; CV +1.5 mm	-0.53 ÷ +0.50 mm	EN ISO 10545-2
6. Edge curvature/Curbura laterala, mm	±0.5/max±2mm	±1.70	CC -1.35 mm; CV +1.35 mm	-0.59 ÷ +0.46mm	EN ISO 10545-2
7. Warpage/Deform area, mm	±0.5/max±2mm	±2.00	CC -1.5 mm; CV +1.5 mm	-0.47 ÷ +0.76mm	EN ISO 10545-2
8. Surface quality/Calitatea suprafetei	≥95% without defects	≥95% without defects	≥95% without defects	Pass	EN ISO 10545-2
9. Water absorption/Absorbt ia de apa, %	≤0,5% Individual ≤0,6%	≤0,5% Individual ≤0,6%	≤0,5%	0.18%	EN ISO 10545-3
10.Modulus of rupture/rezistenta mecanica, thickness<7.5mm, N/mm <sup>2</sup>	≥35N/mm <sup>2</sup> individual≥32N/ mm <sup>2</sup>	≥35N/mm <sup>2</sup> individual≥32N/ mm <sup>2</sup>	≥35N/mm <sup>2</sup>	Average: 57.6N/mm <sup>2</sup>	EN ISO 10545-4
11. Breaking strength, thickness<7.5mm, N /Forta de rupere, N	≥ 700N	≥ 700N	≥ 700N	Average: 1 183N	EN ISO 10545-4

12.Determination of surface abrasion for glazed tiles/Rezistenta la abraziune	the class of abrasive resistance and the number of cycles are declared by producer	the class of abrasive resistance and the number of cycles are declared by producer	Declared value	Class: 3 / 1 500	EN ISO 10545-7
13.Crazing resistance, glazed tiles/Resitenta la crapaturi pentru placi glazurate	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Resistant	EN ISO 10545-11
14.Resistance for household chemicals and swimming pool salts/Rezistenta la solutiile de uz casnic si saruriel de piscina	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	GA	EN ISO 10545-13
15.Resistance to the low concentration acids and alkalis/Rezistenta la acizi si baze de concentratie slaba	Min class B	Min class B	Min class B	GLA	EN ISO 10545-13
16. Resistance to the high concentration acids and alkalis/ Rezistenta la acizi si baze de concentratie mare	Declared value	Declared value	Declared value	GHA	EN ISO 10545-13
17.Stain resistance/Rezistenta la patare	Declared value	Declared value	Declared value	class 5	EN ISO 10545-14
18. Frost resistance/Rezistenta la inghet	Declared value	Declared value	Min class 3	Resistant	EN ISO 10545-12
19.Slipperiness/Rezistenta la alunecare	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	PTV 36+Dry PTV 0-24Wet	CEN/TS 16165
20. MOHS/Rezistenta la zgariere	Declared value	Declared value	Declared value	5	EN 101:1991

Date: 17.01.2020

QC:   
/D. Stancheva/