

TITAN VOLEA. PAINT FOR TENNIS COURTS

Indoor - Outdoor. Matt



Product Code: 181



Description

Protective and decorative paint for indoor and outdoor floors and pavements (concrete, asphalt agglomerate and cork agglomerate). Its most remarkable characteristics are: High adhesion, highly resistant to impacts, weathering resistant, waterproof, quick drying, resistant to abrasion.

Technical Data

Product Type	Acrylic
Finish	Matt
Colour (UNE EN ISO 11664-4)	Green and Red
Density (UNE EN ISO 2811-1)	Green: 1,32 - 1,36 Kg/l / Red: 1,26 - 1,30 Kg/l
Coverage (UNE 48282)	8 - 12 m ² /l
Drying at 23°C 60 % RH (UNE 48301)	30 - 60 minutes
Recoat time at 23°C 60% RH (UNE 48283)	6 - 8 hours
Methods of Application	Brush, roller and spray-gun
Thinner	Water
Equipment Cleaning	Water
Application Temperature, RH<80%	+10 °C - +30 °C. Do not apply if rain is foreseen in the next hours.
Tinting	TITAN Universal Tinting Colours or Water-based Professional Dye
Volume Solids (UNE EN ISO 3233-3)	36 - 41 %
VOC (UNE EN ISO 11890-2)	2.004/42IIA (i) (140/140) Max. COV 18 g/l
Pack sizes	10 l and 4 l

Variations in temperature, humidity, thickness, tinting or surface type, etc. may lead to changes in drying, in coverage or in other properties.

Directions for use

GENERAL REMARKS:

Carefully stir the contents in the pack. The surfaces to be painted have to be clean, dry and sound. Concrete has to be thoroughly hard (it has to be let to dry for at least 28 days).

BARE SURFACES:

If the surfaces are in poor condition, apply a first coat thinned with 10 - 15% water. Apply a second unthinned coat. On surface in poor condition, repair all the damaged areas. Remove all poorly adhered or inconsistent material. Clean all dirt and existing dust. In order to strengthen the surface and achieve uniform porosity, it is recommended to previously apply a base coat of D13 Fixative Primer or A16 Water-based Fixative (outdoors).

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN GOOD CONDITION:

Directly apply the paint after previous washing or brushing. Thin the first coat with 10 - 15% water. Apply a second unthinned coat.

MAINTENANCE OF PREVIOUSLY COATED SURFACES IN POOR CONDITION:

Thoroughly remove old paints and proceed as for bare surfaces.

Precautions

Always read the pack label before use. For more information, please refer to the Safety Data Sheet.

Store in tightly closed containers protected from sources of heat and temperatures below 0°C. Shelf life: 36 months in original unopened packaging.

Waste management:

Follow local legal regulations. Help to protect the environment, do not empty into drains, dispose of this material and its container at hazardous or special waste collection points.

Calculate the amount of product you will need to avoid waste and extra costs.

Collect the leftover material and keep it well stored for a new use.

Issue date: 2019-11

Any technical sheet is automatically cancelled by a subsequent sheet or five years after the issue date. We guarantee the quality of our products. However, we disclaim any liability in relation to factors other than the coating itself or in relation to an unsuitable use or application method. In case of doubt, please refer to our technical service before applying the products.



TITAN

181 - TITAN VOLEA. PAINT FOR TENNIS COURTS

INDUSTRIAS TITAN S.A.U.

España: P. I. Pratenc, c/ 114, 17-19 - 08820 El Prat de Llobregat- T. +34 93 479 74 94

Portugal: Rua Fonte Cova, 51 - 4475-031 Maia
Endereço Postal: Apartado 2020 - 4476-909 Castelo da Maia
T. +351 229 865 450 - F. +351 229 810 764

