

Fisa Tehnica

model ,, Linea "cod intern: 7108; 7110 monoporosa, faianta glazurata, grupa B III,
250x400x8 mm

Testare Standard : EN 14411 Group B III	permissible %	permissible mm	result mm	Metode de testare
1. Lungime mm	+0.6	±2.0	-0.4 + + 0.5	EN ISO 10545-2
2. Latime mm	+0.6	±1.25	-0.15+ + 0.55	EN ISO "10545-2
3. Grosime mm	±10	7.5+ 8.5	7.6 + 8.0	EN ISO 10545-2
4. Liniaritatea muchiei mm	± 0.3	Lungime ± i.2 Latime +0 7fi	-0.5 + 0 -0 7 .;- +0 1	EN ISO 10545-2
5. Rectangularitate mm	±0.5	Lungime ±2.0 Latime ±i .25	-0.7 + +0.4 -0.35 + +0.4	EN ISO 10545-2
6. Curbura centrala mm	+0.5 -0.3	-1.4+ +2.0	+0.55 + +1.5	EN ISO 10545-2
7. Curbura laterala mm	+0.5 -0.3	length -1.2-H2.0 breadth -0.75 ++1.25	+ 0.5 + +1.2 0 + +0.25	EN ISO i 0545-2
8. Deformarea mm	±0.5	±2.0	-0.4 + + 0.35	EN ISO 10545-2
9. Absorbția de apă %	average >10		average i 4.8	EN ISO 10545-3
10. Forta de rupere N	>600		average 586	EN ISO 10545-4
11. Rezistenta mecanica N/mm ²	average >12		average 16.8	EN ISO 10545-4
12. Rezistenta la patare	min class 3		class 5	EN ISO 10545-14
13. Rezistenta la solutii de uz casnic si saruri de piscina	min class GB		class GA	EN ISO 10545-13

Toate placile testate se conformeaza standardului.

