

Technical Data Sheet

Rust-Oleum Polyurethane Finish (400ml spray):
Clear (Gloss, Matt)

A quick-drying, ultra-tough clear finish for use on wood and metal surfaces. Seals, protects and enhances.

Interior Use

Preparation: Ensure surfaces to be painted are free from loose paint, rust, wax, oil and grease. Previously painted surfaces should be abraded to provide a key. Cover surrounding areas to protect from spray mist.

Application: Shake can vigorously for 1 minute after mixing ball begins to rattle, continue to shake regularly during use. Hold can 30cm from surface and spray in a steady back and forth motion, slightly overlapping with each stroke. For best results whilst spraying keep the can the same distance from the surface and keep the can in motion. Apply several light coats a few minutes apart.

Cleaning: After use invert can and spray for 2-3 seconds to clear the spray nozzle.

Drying & Recoating: Touch dry in 2 hours. Hard dry in 24 hours. Drying times are based on warm (15°C), dry application conditions with good ventilation. Lower temperatures and higher humidity will prolong the drying times. 1-2 coats recommended.

Coverage: A 400ml can covers approximately 2m² per coat dependent upon surface profile /porosity.

Limitations: Not for use on vinyl or linoleum, may have a darkening effect on light coloured surfaces. Apply only when temperature is between 10-32°C and relative humidity below 85%. Special precautions should be taken during the surface preparation of pre 1960's paint surfaces over wood and metal as they may contain harmful lead. When dry-sanding avoid dust inhalation by wearing a suitable protective face mask. A copy of the appropriate Health & Safety Data Sheet should be consulted prior to using the product. For further information please contact our Technical Services Department.

Shelf Life: 3 years (unopened) from date of manufacture. (See base of can).

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. It is our recommendation that a trial area is first coated to ensure the product is satisfactory to individual requirements.