



SC KAI CERAMICS SRL
 Sos de Centura nr 13, sat Chiajna, jud. Ilfov
 Tel: +40 31. 437. 82. 23 Fax: +40 31. 432. 99. 54
 Nr. Reg. Com.: J23/621/2013; C.U.I.: RO 19180069;
 Raiffeisen – Sucursala Bucuresti, IBAN: RO49 RZBR 0000 0600 0858 7115

Fisa tehnica

Model „Alba lucioasa” cod intern: 5254

Grupa BIII, 200x300x7 mm

EN 14411:2007 Grupa BIII GL	Toleranța conform 14411:2007 (S > 410 cm ²), %	Toleranța conform 14411:2007 (S > 410 cm ²), mm	Măsurări efectuate în laboratorul KAI, mm	Metoda de testare
1.Lungime, mm	±0,5 %	±1.5 mm	-0,45÷+0,15; +0,1	EN ISO 10545-2
2. Latime, mm	±0,5 %	±1 mm	0÷+0,4, +0,2	EN ISO 10545-2
3.Grosime, mm	±10 %	±6.3÷7.7mm	6,6÷7,5	EN ISO 10545-2
4.Liniaritate, mm	±0,3 %	±0.9 mm	-0,25 ÷ +0,2	EN ISO 10545-2
5.Rectangularitate, mm	±0,5 %	Lungime:±1.5 mm Latime: ±1 mm	Lungime:-0,45÷+0,6 Latime:-0,2÷+0,3	EN ISO 10545-2
6.Curbura centrala, mm	±0,5 %	-1,1÷+1,8 mm	+0,4÷+0,8	EN ISO 10545-2
7.Curbura laterala mm	±0,5 %	Lungime:0,9÷1,5mm Latime:-0,6÷1 mm	Lungime:0,2÷0,6 Latime:-0,15÷0	EN ISO 10545-2
8.Deformare, mm	±0,5 %	±1,18 mm	-0,5÷+0,5	EN ISO 10545-2
9.Absorbția de apă, %	≥10% individual ≥9%	-	Media 12.8% Individual: 10.2%	EN ISO 10545-3
10.Forta de rupere, N	>200 N	-	486.6 N	EN ISO 10545-4
11.Rezistența la încovoiere, N/mm ²	>15 N/mm ²	-	Media: 18.6 N/mm ²	EN ISO 10545-4
12.Rezistența la pete	min. clasa 3	-	clasa 5	EN ISO 10545-14
13. Rezistența la atacul chimic	Mín. Clasa GB	-	Clasa GA	EN ISO 10545-13

