

## FISA TEHNICA

**Colectia** : MAISON BEIGE  
**Produs tip** : Portelanata Glazurata  
**Data raport** : 02.04.2020



| Test Title                          | Test Results  | Requirements               | Desicion |
|-------------------------------------|---|----------------------------|----------|
| Lungime & latime (mm)               | 120/23  | 1198-1220 mm<br>228-232 mm | OK       |
| Grosime (mm)                        | 9   | 8,8 – 9.2 mm               | OK       |
| Unghi curbura (%)                   | ± %0,2  | ± %0,5                     | OK       |
| Rectangularitate (%)                | ± %0,2  | ± %0,6                     | OK       |
| Curbura muchiei (%)                 | ± %0,2  | ± %0,5                     | OK       |
| Curbura coltului (%)                | ± %0,2  | ± %0,5                     | OK       |
| Curbura centrala (%)                | ± %0,2  | ± %0,5                     | OK       |
| Diferente mici de culoare           | Calitatea   | > %95 perfect              | OK       |
| Absorbție apa                       | < 0,5 %   | ≤ 0,5 %                    | OK       |
| Forta spargere (N/mm <sup>2</sup> ) | 40 N/mm <sup>2</sup>  | > 35 N/mm <sup>2</sup>     | OK       |
| Rezistenta abraziune (PEI)          | IV  | Conform                    | OK       |
| Coeff. Expansiune termala           | < 7,0 x 10 <sup>-6</sup>  | Conform                    | OK       |
| Rezistenta termala soc              | Rezistent   | Necesar                    | OK       |
| Rezistenta crapare                  | Rezistent   | Necesar                    | OK       |
| Rezistenta inghet                   | Rezistent   | Necesar                    | OK       |
| Coeficient de frecare               | ~62,0   | Conform                    | OK       |
| Extinderea umiditatii (mm/m)        | < 0,3   | Conform                    | OK       |
| Rezistenta colorare                 | Class 5   | Min. Class 3               | OK       |
| Rezistenta Acid & Alcalin           | GLA   | Necesar                    | OK       |
| Produse chimice uz casnic           | GA  | Min. GB                    | OK       |
| Eliberarea Cadmiului                | < 0,07 mg/dm <sup>2</sup>   | Necesar                    | OK       |
| Eliberare Plumb                     | < 0,8 mg/dm <sup>2</sup>  | Necesar                    | OK       |
| Rezultat                            | Rezultatele sunt pozitive dupa regulile si normele ISO 13006 and EN 14411 standards, Annex G. |                            |          |

SC PREMIER COM SRL

