


| TECHNICAL DATA SHEET | | | |
|---|-----------------------|--|--------------------------|
| FLOORPAN SUN | | 8 MM - CLASS 31 - AC3 | |
| THICKNESS | mm | 8 | EN 13329+A1 |
| WIDTH | mm | 197 | EN 13329+A1 |
| LENGHT | mm | 1205 | EN 13329+A1 |
| SURFACE | | Timberland | |
| EUROPEAN STANDARD | - |  | EN 13329 |
| PACKAGE DETAILS | | | |
| PIECE | 10 piece / 1 package | | |
| M ² | 2,374 m ² | | |
| KG | 16 kg | | |
| PALLET DETAILS | | | |
| PIECE | 60 package / 1 pallet | | |
| M ² | 142,44 m ² | | |
| KG | 960 kg | | |
| CLASS | - | 31 | EN 13329+A1 |
| ABRASION RESISTANCE | - | AC3 | EN 13329+A1 |
| THICKNESS SWELLING | % | ≤18 | ISO 24336 |
| RESISTANCE TO IMPACT | SMALL BALL | N | ≥8 |
| | LARGE BALL | mm | ≥500 |
| WARRANTY DOMESTIC / COMMERCIAL | Years | 10/5 | - |
| RESISTANCE TO STAINING | - | Min. 5 (group 1 and 2) Min. 4 (group 3) | EN 438-2_5 |
| SURCAFE SOUNDNESS | N/mm ² | ≥1.0 | EN 13329+A1 |
| LOCK STRENGTH | LENGHT | kN/m | - |
| | WIDTH | kN/m | - |
| EFFECT OF CASTOR CHAIRA | 25.000 Cycles | No Damage ^a | EN 425:2002 ^b |
| EFFECT OF A FURNITURE LEG | - | No damage shall be visible when tested with foot type 0 | EN 424 |
| OPENING BETWEEN ELEMENTS. (O) | mm | O average ≤ 0,15 mm O max. ≤ 0,20 mm | EN 13329+A1 |
| HEIGHT DIFFERENCE BETWEEN ELEMENTS, (H) | mm | h average ≤ 0,10 mm h max. ≤ 0,15 mm | EN 13329+A1 |
| MOISTURE CONTENT | % | 4-10 | EN 322 |
| FIRE RESISTANCE | Class | C _f S1 | EN 9239-1 |
| FORMALDEHYDE RELEASE | mg/m ² h | ≤3,5 (E1) | EN 12460-3 |