

Quality Certificate
model „MAT” internal code: H 3064
monoporosa, dry pressed, single fired, glazed wall tiles,
group B III, 200x200x6 mm

Testing Standard : EN 14411 Group B III GL	permissible %	permissible mm	result mm	Testing method
1. Length mm	1tile±0.5	1tile±1.0	+0.1÷ +0.3	EN ISO 10545-2
2. Breadth mm	1tile±0.5	1tile±1.0	+0.1÷ +0.3	EN ISO 10545-2
3. Thickness mm	±10	5.5÷ 6.5	6.1÷ 6.3	EN ISO 10545-2
4. Straightness of sides mm	± 0.3	± 0,6	-0.1÷ +0.2	EN ISO 10545-2
5. Rectangularity mm	±0.5	± 1.0	-0.8÷ +0.6	EN ISO 10545-2
6. Centre curvature mm	+0.5	-0.85÷ +1.4	+0.1÷ +0.7	EN ISO 10545-2
7. Edges curvature mm	+0.5	-0.6÷+1.0	-0.2÷ +0.4	EN ISO 10545-2
8. Warpage related to diagonal mm	±0.5	±1.4	-0.2÷ +0.3	EN ISO 10545-2
9. Water Absorption %	average >10 single >9		average 13.9	EN ISO 10545-3
10. Breaking strength N	>200		average 389	EN ISO 10545-4
11. Mechanical strength (modulus of rupture) N/mm ²	average >15		average 19.1	EN ISO 10545-4
12. Resistance to stains	min class 3		class 5	EN ISO 10545-14
13. Resistance to household chemicals and swimming pool salts	min class GB		class GA	EN ISO 10545-13

All the tested tiles COMPLY with the standard.

