



Technical Characteristic KAI/KOS FISA TEHNICA

ODU
16.07.05(9/0)

Model: "Stoneline"
Internal code: 9916;9917;9918;9919;9921;9922
Type: Rectified Porcelain Tiles GL
Group Bla, Nominal size 600 x1200x8.5 mm

Characteristics /Caracteristici Group Bla, Annex G	Tolerance EN / 14411:2016, %	Tolerance / EN14411:2016, mm	Request values/Valori conform standard	Measured in KAI laboratory/Masura tori in laborator Kai	Testing method
1. Work size, mm (Length/width/Lungime /Latime)	±0.6/max±2mm	±2.00	Caliber	Size	EN ISO 10545-2
			8	598 x 1198	
2.Thickness/Grosimea, mm	±5/max±0.5mm	±0.42	8.5 ±0.42 mm	8.4 – 8.6 mm	EN ISO 10545-2
3. Straightness of sides/ Liniaritatea muchiei,mm	±0.5/max±1.5mm	±1.50	±1.40 mm	-0.32 - +0.36 mm	EN ISO 10545-2
4. Rectangularity/ Rectangularitate, mm	±0.5/max±2mm	±2.00	±1.80 mm	-0.31 - +0.41 mm	EN ISO 10545-2
5. Centre curvature/ Curbura centrala, mm	±0.5/max±2mm	±2.00	CC – 0.6 mm; CV + 1.5 mm	+0.11 - +0.93 mm	EN ISO 10545-2
6. Edge curvature/ Curbura laterala, mm	±0.5/max±2mm	±2.00	CC – 0.6 mm; CV + 1.5 mm	+0.07 - +0.90 mm	EN ISO 10545-2
7. Warpage/ Deformarea, mm	±0.5/max±2mm	±2.00	CC – 0.6 mm; CV + 1.5 mm	-0.33 - +0.83 mm	EN ISO 10545-2
8. Surface quality/ Calitatea suprafetei	≥95% without defects	≥95% without defects	95% without defects	Pass	EN ISO 10545-2
9.Water absorption/ Absorbtia de apa, %	≤0,5% Individual ≤0,6%/	≤0,5% Individual ≤0,6% /	≤0,5% Individual ≤0,6% /	0.02 – 0.11 %	EN ISO 10545-3
10.Modulus of rupture /rezistenta mecanica, N/mm²	≥35N/mm² individual≥32N/mm²/	≥35N/mm² individual≥32N/mm²/	≥35N/mm²	Average: 57 N/mm²	EN ISO 10545-4
11. Breaking strength/ Forta de rupere, N	≥1300	≥1300	≥1300	Average: 1864 N	EN ISO 10545-4
12.Determination of surface abrasion for glazed tiles/Rezistenta la abraziune	the class of abrasive resistance and the number of cycles are declared by producer	the class of abrasive resistance and the number of cycles are declared by pro	Declared value	9916 – 4/2100 9917 – 4/6000 9918 – 3/1500 9919 – 3/750 9921 – 3/1500 9922 – 3/750	EN ISO 10545-7

13.Crazing resistance, glazed tiles/Rezistenta la crapaturi pentru placi glazurate	Pass according to EN ISO 10545-1	Pass according to EN ISO 10	Pass according to EN ISO 10	Resistant	EN ISO 10545-11
14.Resistance for household chemicals and swimming pool salts/ Rezistenta la solutiile de uz casnic si saruri de piscina	Min class B	Min class B	Min class B	GA	EN ISO 10545-13
15.Resistance to the low concentration acids and alkalis/Rezistenta la acizi si baze de concentratie slaba	Declared value	Declared value	Declared value	GLA	EN ISO 10545-13
16. Resistance to the high concentration acids and alkalis/ Rezistenta la acizi si baze de concentratie mare	Declared value	Declared value	Declared value	GHA	EN ISO 10545-13
17.Stain resistance/ Rezistenta la patare	Min class 3	Min class 3	Min class 3	class 5	EN ISO 10545-14
18. Frost resistance/ Rezistenta la inghet	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Resistant	EN ISO 10545-12
19. Slipperiness/ Rezistenta la alunecare	Declared value	Declared value	Declared value	PTV 36+ Dry PTV 25-35 Wet	BS 7976
20.MOHS/Rezistenta la zgariere	Declared value	Declared value	Declared value	9	EN 101:1991
21.Slipperiness/Rezistenta la aluneca	Declared value	Declared value	Declared value	R9	DIN 51130

Date: 02.08.2024

