

FISA TEHNICA

Colectia : TAPIAL 40/60
Produs tip : Portelanata Glazurata
Grup produs : Presare uscata / Grup Bla / GL
Data raport : 02.03.2020



Test Title	Test Results	Requirements	Desicion
Lungime & latime (mm)	40/60	147-151 mm 597-601 mm	OK
Grosime (mm)	8,8	8,3 – 8,7 mm	OK
Unghi curbura (%)	± %0,2	± %0,5	OK
Rectangularitate (%)	± %0,2	± %0,6	OK
Curbura muchiei (%)	± %0,2	± %0,5	OK
Curbura coltului (%)	± %0,2	± %0,5	OK
Curbura centrala (%)	± %0,2	± %0,5	OK
Diferente mici de culoare	Calitatea	> %95 perfect	OK
Absorbție apa	< 0,5 %	≤ 0,5 %	OK
Forta spargere (N/mm ²)	40 N/mm ²	> 35 N/mm ²	OK
Rezistenta abraziune (PEI)	IV	Conform	OK
Coeff. Expansiune termala	< 7,0 x 10 ⁻⁶	Conform	OK
Rezistenta termala soc	Rezistent	Necesar	OK
Rezistenta crapare	Rezistent	Necesar	OK
Rezistenta inghet	Rezistent	Necesar	OK
Coefficient de frecare	~62,0	Conform	OK
Extinderea umiditatii (mm/m)	< 0,3	Conform	OK
Rezistenta colorare	Class 5	Min. Class 3	OK
Rezistenta Acid & Alcalin	GLA	Necesar	OK
Produse chimice uz casnic	GA	Min. GB	OK
Eliberarea Cadmiului	< 0,07 mg/dm ²	Necesar	OK
Eliberare Plumb	< 0,8 mg/dm ²	Necesar	OK
Rezultat	Rezultatele sunt pozitive dupa regulile si normele ISO 13006 and EN 14411 standards, Annex G.		

SC PREMIER COM SRL

